



**REX INDUSTRIE-PRODUKTE
GRAF VON REX GMBH**

Telefon +49(0) 7907 / 9620-0
Telefax +49(0) 7907 / 9620-80
e-mail: info@rex-industrie-produkte.de
www.rex-industrie-produkte.de

Technical Data

rex silica fabric 600 g/m² KAR

Composition	:	> 94 % SiO ₂ < 4 % Al ₂ O ₃ Remaining others thermally desized	
Weight	:	600 g/m ²	± 5 %
Standard Width	:	880 mm,	± 30 mm
Thickness	:	0,7 mm	± 0,1 mm

Construction:

Weave	:	satin weave 1/7	
Warp yarn	:	204 tex	
Weft yarn	:	204 tex	
Number of yarns warp	:	19 Fd/cm	± 1 Fd
Number of yarns weft	:	13 Fd/cm	± 1 Fd

Tensile strength

Warp	:	> 1000 N/5 cm
Weft	:	> 700 N/5 cm
Temperature resistance	:	up to 1000°C

The above details, values and information are given according to our best knowledge, have been proven by tests if possible, but are a recommendation without obligation. We in any case recommend tests according to application conditions.

Stand 10/2016