



**REX INDUSTRIE-PRODUKTE
GRAF VON REX GMBH**

Telefon +49(0) 7907 / 9620-0
Telefax +49(0) 7907 / 9620-80
e-mail: info@rex-industrie-produkte.de
www.rex-industrie-produkte.de

Technical Data

thermoglas sewing yarn 22 tex x3x6x3 Niro imp.

Composition	:	Glass	80 %
		stainless steel	10 %
		PU impregnation	10 %
Construction	:	EC 7 22 tex x3x6x3	
R-TEX	:	1485 tex	± 10 %
Tensile strength	:	≥ 300 N	
Twist	:	150 t/m Z	± 20 t/m
Diameter	:	app. 1,20 mm--	
Temperature resistance	:	500°C continuous (short time higher) decomposition of PU starting from 180 °C	
Remarks	:	Kingspool	

The above details, values and information are given according to our best knowledge, have been proven by tests if possible, but are a recommendation without obligation. We in any case recommend tests according to application conditions.

09/2015