



Sort PP Tape	
Base Material	U.V. Treated Polypropylene Film
Adhesion	Water based acrylic pressure sensitive adhesive
Peeling Strength With 180#730	1.8-2.8N/cm
Adhesive to Self	Less than 90 gms/cm
Tensile Strenght	40-50N/cm
Tensile adhesion	4-5N/cm
Elongation	140%
Water vapour resistance	0.17g/m*2-24 hour at 40C
Thermal Behaviour	Stable between -20C to + 100C
Application Temp	-20C to + 40C (dry surface)
Moisture Vapor Transmission Rate	3.9x10 ⁻⁹ g/Pa s m ²