

Isogenopak®

- ⇒ High impact resistance
- ⇒ Will not splinter during riveting
- ⇒ Excellent antistatics
- ⇒ High stiffness
- ⇒ Permanent curl
- ⇒ High chemical resistance
- ⇒ Odor-free
- ⇒ No plasticizers
- ⇒ Physiologically safe in technical applications, including food processing operations
- ⇒ Non-aging and temperature-resistant from -20 °C to +65 °C
- ⇒ Light weight, approx. 500 g/m²
- ⇒ No CFCs or HCFCs used in the making of this product
- ⇒ Made using no silicone
- ⇒ Manufactured without the heavy metals cadmium, lead, chromium^{VI} or their compounds
- ⇒ No flammable drips in the event of a fire
- ⇒ Easy to work, for maximum installation productivity

Insulation Jacketing with permanent curl

Technical data

Property	Value	Unit	Testing method
Tensile impact strength	≥ 400	kJ/m²	DIN EN ISO 8256
Tensile strength	> 35	N/mm²	DIN EN ISO 527
Modulus of elasticity	appr. 1800	N/mm²	DIN EN ISO 527
Water vapour resistance μ	appr. 60000	-	DIN 52615
Linear heat expansion coefficient	1,5 x 10 ⁻⁴	1/K	Leitz-Dilatometer
Thermal conductivity	appr. 0.16	W/mK	at 20°C
Emissivity ε	97	%	ISO 10292 annex A
Film type	K201/01-75/7900-281		
Material	Rigid PVC		
Colour	Isogenopak®-grey (close to RAL 7035/7047)		
Isogenopak® meets the requirements of DIN EN 15701.			

Fire performance

- DE: Building materials class DIN 4102-B2
- AT: Classification acc. ÖNORM A 3800 Part 1: B1, Q1
- IT: DD.MM. 26/06/84: Classe 1

Supply dimensions

Thickness: 0.35 mm	Width: 1000 mm	Length: 15m / 25m / 35m
--------------------	----------------	-------------------------

Installation notes

- Attach with plastic rivets spaced approx. 20 cm apart or solvent-based adhesive.
- Isogenopak® is not recommended for outdoor use (UV exposure).

Customs tariff number: 39 20 49 10

www.isogenopak.com

Klöckner Pentaplast GmbH & Co. KG, Gendorf Works, DE-84504 Burgkirchen, Germany
 Tel. +49 (0) 8679 / 75510 Fax +49 (0) 8679 / 7 5096

The information presented here is current as of the printing date. Please ask for the latest version of this brochure, if available. No warranty is expressed or implied herein with respect to specific product properties or fitness of the products for a particular use. Industrial property rights are to be observed.

We warrant a quality free of defects within the context of the General Terms of Sale of Klöckner Pentaplast GmbH & Co. KG 08/2011 SJ